



Tabla de acabados hojalata y TFS: / Tinplate and TFS finish:

Product finish	Steel base	Tinplate/ECCS	Flow-melted	Nominal surface roughness of the steel base $\mu\text{m Ra}$
Bright	Smooth	Tinplate	Yes	$\leq 0,35$
Fine stone	Fine stone	Tinplate	Yes	0.25-0.45
Fine stone	Fine stone	ECCS	-	0.25-0.45
Stone	Stone	Tinplate	Yes	0.35-0.60
Stone	Stone	Tinplate	Yes	0.35-0.60
Silver	Shot blast	Tinplate	Yes	≥ 0.90
Matt	Shot blast	Tinplate	No	Various

Goldium Steel S.L.

Avda. de La Rioja, 6 -3º
 26001 • Logroño • La Rioja • España
 Teléfono: +34 941 048 023
 Fax: +34 941 942 148
 Movil: +34 609 786 598
info@goldium.es
www.goldium.es