



Valores de dureza Rockwell HR 30 Tm para chapas de simple reducción (sólo a título indicativo)  
/ Rockwell HR 30 Tm hardness values for single reduced plate (for guidance only)

Thickness (mm)	≤0,21	0,21 to ≤0.28	>0.28
Grade	Nominal (Deviation)	Nominal (Deviation)	Nominal (Deviation)
TS230	Max 53	Max 52	Max 51
TS245	53 (±4)	52 (±4)	51 (±4)
TS260	56 (±4)	55 (±4)	54 (±4)
TS275	58 (±4)	57 (±4)	56 (±4)
TS290	60 (±4)	59 (±4)	58 (±4)
TH415	62 (±4)	61 (±4)	60 (±4)
TH435	65 (±4)	65 (±4)	64 (±4)

Goldium Steel S.L.

Avda. de La Rioja, 6 -3º  
26001 • Logroño • La Rioja • España  
Teléfono: +34 941 048 023  
Fax: +34 941 942 148  
Movil: +34 609 786 598  
info@goldium.es  
www.goldium.es