



Propiedades Mecánicas: / Mechanical properties:

Annealing	Grade	Yield/0,2% Proof strength (Rp) N/mm ² Nominal values (Dev. ±50)	Tensile strength (Rm) N/mm ² Aim values (Dev. ±50)
Batch	TS230	230	325
Batch	TS245	245	340
Batch	TS260	260	360
Batch	TS275	275	375
Batch	TS290	290	390
Batch	TS550	550	575
Continuous	TH415	415	435
Continuous	TH435	435	460
Continuous	TH520	520	540
Continuous	TH550	550	570
Continuous	TH580	580	590
Continuous	TH620	620	625

Goldium Steel S.L.

Avda. de La Rioja, 6 -3º
26001 • Logroño • La Rioja • España
Teléfono: +34 941 048 023
Fax: +34 941 942 148
Movil: +34 609 786 598
info@goldium.es
www.goldium.es